

Estetic[®] Lighting 82

Properties	<ul style="list-style-type: none"> • Very high reflectance • Good formability • Thermosetting paint • Surface treatment and paint: free of hexavalent chromium and heavy metals
-------------------	---

Applications	Lighting																				
Description	<table> <tr> <td>Thickness ⁽¹⁾</td> <td>25 microns</td> </tr> <tr> <td>Composition</td> <td>Front: 5 microns primer + 20 microns top coat Back: 5, 7, 10 or 12 microns backing coat</td> </tr> <tr> <td>Gloss (Gardner 60°) ⁽¹⁾</td> <td>Usual: 50-90 GU</td> </tr> <tr> <td>Light reflectance (Y)</td> <td>≥ 82</td> </tr> <tr> <td>Colours</td> <td>Various shades of white</td> </tr> <tr> <td>Appearance</td> <td>Smooth</td> </tr> <tr> <td>Temporary protection (optional)</td> <td>Self-adhesive film or heat-sealed film</td> </tr> </table>	Thickness ⁽¹⁾	25 microns	Composition	Front: 5 microns primer + 20 microns top coat Back: 5, 7, 10 or 12 microns backing coat	Gloss (Gardner 60°) ⁽¹⁾	Usual: 50-90 GU	Light reflectance (Y)	≥ 82	Colours	Various shades of white	Appearance	Smooth	Temporary protection (optional)	Self-adhesive film or heat-sealed film						
Thickness ⁽¹⁾	25 microns																				
Composition	Front: 5 microns primer + 20 microns top coat Back: 5, 7, 10 or 12 microns backing coat																				
Gloss (Gardner 60°) ⁽¹⁾	Usual: 50-90 GU																				
Light reflectance (Y)	≥ 82																				
Colours	Various shades of white																				
Appearance	Smooth																				
Temporary protection (optional)	Self-adhesive film or heat-sealed film																				
Performance	<table> <tr> <td>Adhesion of the coating (T-bend)</td> <td>0.5 T</td> </tr> <tr> <td>Resistance to cracking on bending (T-bend)</td> <td>2 T</td> </tr> <tr> <td>Impact resistance</td> <td>18 J</td> </tr> <tr> <td>Surface "pencil" hardness</td> <td>HB to F</td> </tr> <tr> <td>Salt spray test</td> <td>240 hours</td> </tr> <tr> <td>Condensation resistance: <ul style="list-style-type: none"> • QCT test • Corrosion protection category </td> <td>1000 hours CPI3</td> </tr> <tr> <td>Compliance with European directives 2002/95/EC and 2011/65/EC on electrical and electronic equipment</td> <td>ROHS-compliant</td> </tr> <tr> <td>Resistance to acids and bases</td> <td>Good to very good</td> </tr> <tr> <td>Resistance to solvents: <ul style="list-style-type: none"> • Aliphatics and alcohols • Ketones • Aromatics </td> <td>Good to very good Low Good to very good</td> </tr> <tr> <td>Resistance to mineral oils</td> <td>Very good</td> </tr> </table>	Adhesion of the coating (T-bend)	0.5 T	Resistance to cracking on bending (T-bend)	2 T	Impact resistance	18 J	Surface "pencil" hardness	HB to F	Salt spray test	240 hours	Condensation resistance: <ul style="list-style-type: none"> • QCT test • Corrosion protection category 	1000 hours CPI3	Compliance with European directives 2002/95/EC and 2011/65/EC on electrical and electronic equipment	ROHS-compliant	Resistance to acids and bases	Good to very good	Resistance to solvents: <ul style="list-style-type: none"> • Aliphatics and alcohols • Ketones • Aromatics 	Good to very good Low Good to very good	Resistance to mineral oils	Very good
Adhesion of the coating (T-bend)	0.5 T																				
Resistance to cracking on bending (T-bend)	2 T																				
Impact resistance	18 J																				
Surface "pencil" hardness	HB to F																				
Salt spray test	240 hours																				
Condensation resistance: <ul style="list-style-type: none"> • QCT test • Corrosion protection category 	1000 hours CPI3																				
Compliance with European directives 2002/95/EC and 2011/65/EC on electrical and electronic equipment	ROHS-compliant																				
Resistance to acids and bases	Good to very good																				
Resistance to solvents: <ul style="list-style-type: none"> • Aliphatics and alcohols • Ketones • Aromatics 	Good to very good Low Good to very good																				
Resistance to mineral oils	Very good																				
Remarks	<p>These performance characteristics refer specifically to metallic coating Z100. If any product (film, oil, foam, glue, paint etc) is to be applied after coil delivery, compatibility with the coating needs to be checked first.</p>																				

(1) Nominal value, tolerance according to EN 10169